

Section 4119. Pipe Backfill Material Under Interstate and Primary Roadways.

4119.01 DESCRIPTION.

Aggregate of the following types:

- Crushed Stone,
- Gravels for which 75% or more of the particles retained on the 3/8 inch (9.5 mm) sieve have at least one fractured face as defined in [Materials I.M. 305](#) (the fractured face requirement shall only apply to bedding material placed under Primary or Interstate roadways), or
- Crushed PCC, if approved by the Engineer.

4119.02 CRUSHED STONE.

Meet the requirements of [4120.04](#).

4119.03 CRUSHED GRAVEL.

Meet the requirements of [4120.03](#).

4119.04 CRUSHED PCC.

Meet the requirements of [Materials I.M. 210](#) and for Gradation No. 11 of the [Aggregate Gradation Table, Article 4109.02 \(Appendix\)](#).