

## Section 4120. Granular Surfacing and Granular Shoulder Aggregate

### 4120.01 DESCRIPTION.

Uniform mixture of fine and coarse particles of crushed stone, gravel, or a combination of these materials with sand. Crushed recycled materials are to total no more than:

- 30% of the shoulder aggregate for new construction.
- 50% of the total for existing granular shoulders.

### 4120.02 GRANULAR MATERIAL.

#### A. Granular Surfacing.

Furnish material meeting the requirements of [Article 4120.04](#), or when specified in the contract documents, meet the requirements of [Article 4120.03](#), [4120.05](#), or [4120.06](#).

#### B. Granular Shoulders.

1. Furnish material meeting the requirements of [Article 4120.04](#) or recycled materials. When specified in the contract documents, meet the requirements of [Article 4120.05](#) or [4120.06](#). For recycled materials, meet the following requirements:
  - Recycle PCC, RAP, or composite pavements to meet the requirements of [Materials I.M. 210](#).
  - Crush PCC or composite pavement to meet the requirements for Gradation No. 11 of the Aggregate Gradation Table, [Article 4109.02](#).
  - Process RAP to pass the 1.5 inch (37.5 mm) sieve.
2. The contract documents may allow a Class C gravel and crushed aggregate mixture for granular shoulders meeting the following:
  - 30% to 50% crushed stone meeting soundness and abrasion requirements of [Article 4120.05](#). Meet the requirements for Gradation No. 10 of the Aggregate Gradation Table, [Article 4109.02](#) with the exception of 8% to 16% passing the No. 200 (75  $\mu$ m) sieve.
  - 30% to 50% recycled crushed PCC or composite materials meeting the above requirements for Granular Shoulders. Meet the requirements for Gradation No. 10 of the Aggregate Gradation Table, [Article 4109.02](#) with the exception of 8% to 16% passing the No. 200 (75  $\mu$ m) sieve.
  - 30% to 50% RAP processed to pass the 1.5 inch (37.5 mm) sieve.

### 4120.03 CLASS C GRAVEL.

Meet the requirements for gradation No. 10 of the Aggregate Gradation Table, [Article 4109.02](#) and Table 4120.03-1:

**Table 4120.03-1: Coarse Aggregate Quality (Class C Gravel)**

Coarse Aggregate Quality	Maximum Percent Allowed	Test Method
C Freeze	15	Office of Materials Test Method No. Iowa 211, Method C
Shale (+ No. 4 (4.75mm) sieve)	10	<a href="#">Materials I.M. 372</a>
Total of Clay Lumps and Friable Particles, plus % passing No. 200 (75µm) sieve	15	<a href="#">Materials I.M.s 368 and 306</a>
Total of Shale, Clay lumps and friable particles, plus % passing. No. 200 (75 µm) sieve	20	<a href="#">Materials I.M.s 372, 368, and 306</a>

**4120.04 CLASS A CRUSHED STONE.**

Meet the requirements for Gradation No. 11 of the Aggregate Gradation Table, [Article 4109.02](#) and Table 4120.04-1:

**Table 4120.04-1: Coarse Aggregate Quality (Class A Crushed Stone)**

Coarse Aggregate Quality	Maximum Percent Allowed	Test Method
Abrasion	45	AASHTO T 96
C Freeze	15	Office of Materials Test Method No. Iowa 211, Method C
Clay Lumps and Friable Particles	4	<a href="#">Materials I.M. 368</a>
Note: For shoulders only, abrasion limits may be raised to 55 if Alumina does not exceed 0.7 or A Freeze does not exceed 10.		

**4120.05 CLASS B CRUSHED STONE.**

Meet the requirements for Gradation No. 11 of the Aggregate Gradation Table, [Article 4109.02](#) and Table 4120.05-1:

**Table 4120.05-1: Coarse Aggregate Quality (Class B Crushed Stone)**

Coarse Aggregate Quality	Maximum Percent Allowed	Test Method
Abrasion	55	AASHTO T 96
C Freeze	20	Office of Materials Test Method No. Iowa 211, Method C
Total of Abrasion & C Freeze	65	
Clay Lumps and Friable Particles	4	<a href="#">Materials I.M. 368</a>

**4120.06 CLASS D CRUSHED STONE.**

Refer to the contract documents for gradation and quality requirements.

**4120.07 AGGREGATE FOR PAVED SHOULDER FILLETS.**

Crushed stone or recycled materials meeting the requirements for Gradation No. 11 of the Aggregate Gradation Table, [Article 4109.02](#), and meeting the quality requirement of [Article 4120.04](#). For recycled materials, meet the requirements of [Article 4120.02, B](#).