

Section 4137. Asphalt Binder

4137.01 GENERAL REQUIREMENTS.

- A. Meet the requirements for the type and grade specified in the contract documents.
- B. Determine performance grade according to AASHTO R 29.
- C. Do not add acids to modify asphalt binders.
- D. For asphalt binder grades with a temperature spread of 92° or greater, use binders that meet the PG+ requirements established by the Combined State Binder Group as follows:

Table 4137.01-1: PG+ Requirements

Temperature Spread^{1,2}	92	98	104
Elastic Recovery: AASHTO T 301 at 77° F. (RTFO Aged AASHTO T 240)	65% min.	65% min.	65% min.
DSR Phase Angle; degrees (original binder)	77.0 max.	75.0max.	73.0 max.
<p>1 Temperature spread is determined by subtracting low temperature from high temperature; for example PG 64-28: 64 - (-28) = 92</p> <p>2 When a grade change is required to compensate for binder in recycled materials, the virgin binder provided shall meet the above requirements for the original grade specified in the contract documents.</p>			