Sampling & Testing Guide-Minimum Frequency

April 19, 2011 Supersedes October 21, 2008

BASE REPAIR (2212), PAVEMENT REPAIR (PATCHES) Sections 2529 & 2530

Matls. IM 204 Appendix T

MATERIAL OR CONSTRUCTION	TESTS	METHOD OF ACCEPTANCE & RELATED IMS		QUALITY CONTROL						INDEPENDENT ASSURANCE & VERIFICATION S&T						
ITEM			SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT			
SOURCE INSPEC	CTION															
Aggregates Fine (4110)		AS 20	9													
Aggregates Coarse (4115)		AS 20	9													
Portland Cement (4101)	Quality	AS 40														
Fly Ash (4108)	Quality	AS 491.1	7													
GGBFS (Ground Granulated Blast Furnace Slag)	Quality	AS 491.1	4													
Curing Compound (4105)	Lab Tested	40	5													
Air Entraining Admixture (4103)	Quality	AS 40	3													
Granular Backfill	Gradation Quality	AS CERT AS CERT														
Drain Tubing	Quality	AS 44	3													
Epoxy Grout		AS 491.1	1													
Joint Seal (4136.02)	Lab Tested	436.0 AS 436.0														
Backer Rod (4136.02)		AS 436.0	4													
Steel Reinforcing	Quality	AS 45	1													
AS-Approved Sourc ASD-Approved Sho S&T-Sampling & Te	p Drawing		Cert A-Typ Cert C-Typ Cert D-Typ	e C Certi	fication		DME-Dist	rict Materia ntral Mater	ls Enginee	l gineer/Pr r	 oject Engine	eer	IA-Independ V-Verificatio	dent Assurance on		

Sampling & Testing Guide-Minimum Frequency

April 19, 2011 Supersedes October 21, 2008

BASE REPAIR (2212), PAVEMENT REPAIR (PATCHES) Sections 2529 & 2530

Matls. IM 204 Appendix T

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE &		QUA	LITY CONTRO	DL			REMARKS					
		RELATED IMs	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	
PLANT INSPECT	ION													
Aggregates-Coarse (4115)	Grad	302 306 336	CONTR	1/lot	IM 301	CONTR		V	RCE/ CONTR	Sample 1/wk Test 1 st day +20%	IM 301	RCE		
Moist		308	CONTR	1 / half day	1000 gm	CONTR				.2070				
Sp.	Gr.	307	CONTR	IM 527	1000 gm	CONTR								
Quality		AS 209												
Aggregate- Fine (4110)	Gradation	302, 306 336	CONTR	1/lot	IM 301	CONTR	830211	V	RCE/ CONTR	Sample 1/wk Test 1 st day+ 20%	IM 301 IM 301	RCE		
Moisture		308, 528	CONTR	1/lot	IM 301	CONTR	830211							See IM 528 if Moisture Probe is used
Sp.	Gr.	307	CONTR	IM 528	IM 301	CONTR	830211							
Quality		AS 209												
Portland Cement (4101)	Quality	AS CERT D		Each Load										
Fly Ash	Quality	AS CERT D		Each Load										
Air Entraining Admixture		AS 403						V	DME 1/batc	1	1 pt	CTRL		Sample lots not previously
Water Reducing Admixture		AS 403						V	DME 1/batc	1	1 pt	CTRL		reported or as directed by DME
Retarding Admixture		AS 403						V	DME 1/batc	1	1 pt	CTRL		
AS-Approved Sourc ASD-Approved Sho S&T-Sampling & Te	p Drawing		ert C-Type	A Certificatio C Certificatio D Certificatio htractor	n		DME-Dist		ls Engineer	neer/Project E	Engineer		IA-Indepen V-Verificati	dent Assurance on

Sampling & Testing Guide-Minimum Frequency

April 19, 2011 Supersedes October 21, 2008

BASE REPAIR (2212), PAVEMENT REPAIR (PATCHES) Sections 2529 & 2530

Matls. IM 204 Appendix T

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE &			QUA	ALITY CONTR	OL		INDEPENDENT ASSURANCE, & VERIFICATION S&T						
		RELATED IM	S	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	
GRADE INSPEC	TION	•		•		•			•	•				•	•
Uncompacted HMA Mixture		Scale ticket with JMI number	F												Job Mix Formula (JMF) approved by DME
Plastic Concrete	Air Slump	318 317	327 327						V V	RCE RCE	1/30 cy 1/30 cy		RCE RCE		Minimum 1 per pour
Reinforcing Steel Epoxy-Coated Steel	Quality Quality	AS AS	451 451	Each	Shipment										
Calcium Chloride	Concentr.		373	RCE 1/lot			RCE								
Smoothness for Compacted HMA or Hardened Conc. (2529.10)			341	CONTR			CONTR								Approval by DME See Plans/Specs for exclusions
ASD-Approved Shop Drawing C			Cert C-Type C Certification DME-Dist Cert D-Type D Certification CTRL-Ce					esident Construction Engineer/Project Engineer IA-Independ District Materials Engineer V-Verificatio Central Materials Office R-Contractor						dent Assurance on	