

Section 4134. Floodable Backfill Material

4134.01 DESCRIPTION.

Uncrushed natural sand and gravel or natural sand.

4134.02 GRADATION.

- A. For natural sand and gravel use Gradation No. 35 of the [Aggregate Gradation Table, Article 4109.02](#).
- B. For natural sand use Gradation No. 36 of the [Aggregate Gradation Table, Article 4109.02](#).

4134.03 QUALITY.

For crushed stone, meet the requirements of Table 4134.03-1:

Table 4134.03-1: Aggregate Quality (Floodable Backfill Material)

Coarse Aggregate Quality	Maximum Percent Allowed	Test Method
Abrasion	55	AASHTO T 96
C Freeze	20	Office of Materials Test Method No. Iowa 211, Method C
Total of Abrasion & C Freeze	65	---
Clay Lumps and Friable Particles	4	Materials I.M. 368