

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMs	QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡➡
			SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	
SOURCE INSPECTION													
Aggregate-Fine (4110)		AS 209											
Aggregate-Coarse (4115)		AS 209											
Granular Backfill (4133)		AS 209											
Portland Cement (4101)	Quality	AS 401											
Fly Ash (4108)	Quality	AS 491.17											
Mixing Water (4102)	Quality		RCE	➡➡ 1/project	1 L	CTRL	731						Not required for potable water from Municipal Supply
GGBFS (Ground Granulated Blast Furnace Slag)	Quality	AS 491.14											
Air Entraining Admixture	Quality	AS 403											
Retarding Admixture	Quality	AS 403											
Water reducing Admixture	Quality	AS 403											
Curing Compound (4105)	Lab Tested	AS 405 ➡➡	DME	1/lot	1 L	CTRL							Bridge Barrier Rails AASHTO, M148, Cert. by Manufacturer
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing		Cert A-Type A Certification Cert C-Type C Certification Cert D-Type D Certification											
			RCE-Resident Construction Engineer/Project Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor					ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor					

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMS		QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡➡
				SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	
SOURCE INSPECTION														
Pre-formed Joint Sealer (4136)	Lab-Tested	AS	436.02 436.05											
Reinforcing Steel Bars (4151)	Quality	AS	451											
Steel Pile (4167)	Quality		467											
Concrete Pile (4166)	Quality	AS	570											
Timber Pile (4165)	Quality	Cert A AS	462											DME may obtain monitor samples. Charge numbers on butt end.
Timber (4162) & Lumber (4163)		Cert A AS	462											DME may obtain monitor samples
Concrete Anchors	Quality	AS	453.09											
Epoxy Grout	Quality	AS	491.11											
Concrete Sealer	Quality	AS	491.12											
Subdrain Pipe (4143)	Quality	AS	443, 448											
Neoprene Bearing Pads (4195)		AS	495.03											
Bronze Bearing Plates (4190.03)		AS D/Cert A												
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing		Cert A-Type A Certification Cert C-Type C Certification Cert D-Type D Certification							RCE-Resident Construction Engineer/Project Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor					ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMs	QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡➡	
			SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPL SIZE	TEST BY		REPORT
SOURCE INSPECTION														
Steel Masonry Plate (4152)		AS Drawing/Cert A												
Precast Units (2407)	Quality	AS 570												
Anchor Bolts (lighting, signing, handrail) (4153)	Lab Tested	ASD												
Structural Steel (4152)	Quality	➡➡ Cert A												Monitor Sample According to plans or other instructions
Aluminum Bridge Rail & Anchor Assembly		ASD												
Conduit (Electrical) (4185.10) Steel		AS												
Conduit (Plastic) (4185.10)	Lab Tested		DME	1/size	4'	CTRL								
Bentonite		Visual												
Flowable Mortar	Lab Tested ➡➡	Approved Trial Mix 525, 375												Tested by DME
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing		Cert A-Type A Certification Cert C-Type C Certification Cert D-Type D Certification			RCE-Resident Construction Engineer/Project Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor			ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor						

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMs	QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡➡		
			SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPL E SIZE	TEST BY		REPORT	
PLANT INSPECTION															
Aggregate- Fine (4110)	Gradation	302, 306 336	CONTR	3/lot	IM 301	CONTR	800240	ASSUR CORR	DME CONTR	1/1000 cy➡➡ 1 st day +10%	IM 301 IM 301	DME RCE		System Approach Applicable	
	Moisture	➡➡ 308, 528	CONTR	1/lot	1000 gm	CONTR								See IM 528 if Moisture Probe is used	
	Sp. Gr.	307	CONTR	IM 528	1000 gm	CONTR									
	Quality	AS 209													
Aggregate- Coarse (4115)	Gradation	302, 306 336	CONTR	3/lot	IM 301	CONTR			ASSUR CORR	DME CONTR	➡➡ 1/1000 CY 1 st day+10%	IM 301 IM 301	DME RCE		System Approach Applicable
	Moisture	308, 528	CONTR	1/lot	2000gm	CONTR									
	Sp. Gr.	307	CONTR	IM 528	2000gm	CONTR									
	Quality	AS 209							V	DME	1/1000 cy	50 lb	CTRL		
Portland Cement	w/c ratio	528	CONTR	1/pour		CONTR									
	Quality	AS Cert D							V	DME	1/1000 cy	15 lb	CTRL		
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing		Cert A-Type A Certification Cert C-Type C Certification Cert D-Type D Certification		RCE-Resident Construction Engineer/Project Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor				ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor							

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMs		QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡➡
				SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	
PLANT INSPECTION														
Fly Ash	Quality	AS	Cert D		Each Load			800240						
GGBFS(Ground Granulated Blast Furnace Slag)	Quality	AS	Cert D		Each Load									
Air-Entraining Admixture (4103)		AS	403	RCE	1/lot➡➡	0.5 L	CTRL							Sample lots not previously reported or as required by DME
Retarding Admixture		AS	403	RCE	1/lot➡➡	0.5 L	CTRL							
Water Reducing Admixture (4103)		AS	403	RCE	1/lot➡➡	0.5 L	CTRL							
GRADE INSPECTION														
Plastic Concrete	Air Content	316, 327		RCE	1/30 cy➡➡		RCE	E145*	ASSUR	DME	1/1000 cy		DME	DME may adjust
	Slump	317, 327		RCE	1/30 cy➡➡		RCE		ASSUR	DME	1/1000 cy		Witness Only	DME may adjust
	Beams	316, 327, 328		RCE	2/placement➡➡		RCE							If required per 2403.18 and 2403.19
	Cylinders									DME		➡➡ 3/project		DME
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing		Cert A-Type A Certification Cert C-Type C Certification Cert D-Type D Certification		RCE-Resident Construction Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor				ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor						

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.

*Available from the Office of Construction.

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMs	QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡➡	
			SAMPLE BY	FREQ.	SAMPLE SIZE	TES BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY		REPORT
GRADE INSPECTION														
Reinforcing Steel (4151)	Quality	AS Cert A		Each Shipment			Field Book	V	DME	IM 451	6 ft	CTRL		
Reinforcing Steel Epoxy Coated (4151)	Quality	AS Cert A		Each Shipment			Field Book	V ➡➡	DME	1 of largest bar in deck	6 ft	CTRL		Will be acceptance tested for coating
Steel Pile (4167)	Quality	AS Cert A		Each Heat			Field Book		DME	IM 467		CTRL		Monitor by CTRL Materials
Timber Pile (4165)	Quality	462						MON						No grade requirement
Anchor Bolts (lighting, signing, handrail)	Lab Tested	ASD		➡➡ 1/project	1 bolt w/nut & washer		CTRL							Sample only if not source inspected
Steel Masonry Plates (4152)		ASD Cert A		Each Shipment			Field Book							Approved by Materials Department
Bronze Bearing Plates (4190.03)	Lab Tested			➡➡ 1/project	1 only		CTRL							Sample only if not source inspected
Neoprene Bearing Pads (4195)		AS 495.03		Each Shipment			820905							
Alum. Bridge Rail & Anchor Assembly		ASD		Each Shipment			Field Book							Approved By Materials Dept.
Drains (Std Steel Pipe)(as per plan)	Dimensions Galvanized	ASD Visual 332		1/project			DME Test Report							
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing			Cert A-Type A Certification Cert C-Type C Certification Cert D-Type D Certification			RCE-Resident Construction Engineer/Project Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor			ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor					

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.

Sampling & Testing Guide-Minimum Frequency

**STRUCTURAL CONCRETE, REINFORCEMENT, FOUNDATIONS & SUBSTRUCTURES,
CONCRETE STRUCTURES, CONCRETE FLOORS, & CONCRETE BOX,
ARCH & CIRCULAR CULVERTS**

Matls. IM 204
Appendix H (US) Units

Sections 2403, 2404, 2405, 2406, 2412, & 2415

October 18, 2005
Supersedes April 19, 2005

MATERIAL OR CONSTRUCTION ITEM	TESTS	METHOD OF ACCEPTANCE & RELATED IMs	QC/ACCEPTANCE S&T					ASSURANCE, CORRELATION & VERIFICATION S&T					REMARKS ➡	
			SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY	REPORT	S&T TYPE	SAMPLE BY	FREQ.	SAMPLE SIZE	TEST BY		REPORT
GRADE INSPECTION														
Timber (4162) & Lumber (4163)	Quality	Visual 462												
Subdrain Pipe (4143)	Quality	AS Cert D 443, 448		Each Shipment										
Flowable Mortar (2506) ➡	Flow Test	375	RCE	As needed for Project Control		RCE	830211							Mix Design approval by DME
Bentonite	Flow Test	Visual 375				RCE								
Smoothness (2317)	Profilometer	Cert. Test Report 341	CONTR	Each Project	Each Wheelpath	CONTR	821301	CORR	DME	10%				
AS-Approved Source ASD-Approved Shop Drawing S&T-Sampling & Testing			Cert A-Type A Certification Cert B-Type C Certification Cert C-Type D Certification			RCE-Resident Construction Engineer/Project Engineer DME-District Materials Engineer CTRL-Central Materials Office CONTR-Contractor			ASSUR-Independent Assurance VERIF-Verification CORR-Correlation MON-Monitor					

Verification/Assurance samples not required when mix quantity is less than 50 cu. yd.

NOTE: When the Project Engineer does the acceptance gradation testing, the assurance sample is to be split with the Project Engineer. This split sample is for correlation purposes and, if it is not a routine lot sample, should not be used for determining specification compliance of a lot. However, any non-compliant test result is to be resolved.