## **TABLE D**

## Price Adjustment Schedules for Bridge Floor Resurfacing & Overlay Projects

Percent Payment

Density	Percent Payment
97.5% and Over	100%
97.4% - 97.0%	50%
96.9% and Below	Remove and replace

Oldinp	ranget 20 mm(/4 )	r crociit i dyillelit
0–25 mm (0 – 1")		100%
30-40 mm (1 ¼" –	1 ½")	50%
Over 40 mm (Over 1 ½")		Remove and replace

Target 20 mm(3/2")

Air Content		
Percent Air	Target 6.5%	Percent Payment
Less than 4.0%		Remove and replace
4.0% - 4.4%		0%
4.5% - 4.9%		50%
5.0% - 5.4%		75%
5.5% - 7.5%		100%
7.6% - 8.0%		75%
8.1% - 8.5%		50%
8.6% - 9.0%		0%
9.1% and Over		Remove and replace

## **Determining Deficient Area**

Slumn

An overlay density test will be representative of the width placed and:

- For a distance extending one-half the distance to the next density test location measured along center line, or
- To the end section if project is starting or ending.

Air and slump will be considered complying for all mix placed since the last complying test. (Assumes concrete placed since the last previous complying test is in compliance until the noncomplying test occurs.) When a noncomplying test is identified, much more frequent testing is warranted.

01/29/01 Appendix 2-34(D)